



Braycote 601 EF

Grease, Rust Preventive, Rocket Propellant Compatible

Description

Castrol Braycote™ 601 EF is a smooth, buttery, translucent, off-white, NLGI #2 grease. Its base oil (Castrol Brayco® 815Z) is a perfluorinated polyether, with exceptional chemical resistance, extremely low volatility, and a wide temperature service range. The grease is non-toxic, nonflammable, and does not use any chlorofluorocarbons (CFC's) during product manufacture. This product exhibits unusually high load-carrying capabilities as measured by the Four-Ball EP Test, and contains a rust and corrosion inhibitor for extra component protection.

Application

Braycote 601 EF is designed to operate in the presence of rocket fuels and oxidizers and high vacuum. It is frequently used in space applications including the Space Shuttle and satellites. It should also be considered in any application where a hostile chemical or extreme environmental conditions would preclude the use of an ordinary grease. Typical applications include ball and roller bearings, gears, and as an assembly lubricant for O-rings and elastomers. Perfluorinated greases, such as this product, exhibit excellent shelf life due to their intrinsic inertness.

Additional Information

Temperature Range
-80°C to 204°C (-112°F to 400°F)

Castrol Fluoroclean™ X100 or Castrol Fluoroclean™ HE can be used to remove this lubricant. Refer to the data sheets for these products for information regarding these products.

Limitations

Braycote 601 EF is compatible with most commonly utilized materials, plastics, and elastomers. It may be adversely affected by Lewis Acid Catalysts such as aluminum chloride, at elevated temperatures. Newly exposed rubbing surfaces of aluminum, magnesium and titanium alloys may react with this product under certain conditions. Such systems should be thoroughly evaluated. Surfaces must be well cleaned of organic rust inhibitors prior to grease application to insure proper lubrication. This product is not recommended for use in applications under high vacuum with loads exceeding 100,000 psi for extended periods of time.

Typical Characteristics

Name	Method	Units	Braycote 601 EF
Unworked Penetration	ASTM D217 / IP 50	0.1 mm	270 - 295
Worked Penetration (60 strokes @ 25°C / 77°F)	ISO 2137 / ASTM D217	0.1 mm	270 - 295
Oil Separation (30 hrs @ 204°C / 400°F)	ASTM D6184 / FTM 321.2	% wt	11
Rust Test (distilled water)	ASTM D1743	-	Pass
Copper Corrosion (24 hrs, 100°C / 212°F)	ASTM D4048	Rating	1b
Four Ball Wear test - Wear Scar Diameter (40 kgf / 75°C / 1200 rpm / 1 hr)	DIN 51350 / ASTM D2266	mm	0.9
Dropping Point	ASTM D2265	°C/°F	213 / 415
Four Ball Weld Load test - Weld Point	ISO 11008 / ASTM D2596	N	>8000
Vacuum Stability	ASTM E595 / NASA SP-R-0022A	Total Weight Loss (% wt) / Volatiles (%wt)	0.36/0.03
Low temperature Torque - starting torque @ -62°C / -80°F	ASTM D1478	Nm	0.06
Low temperature Torque - torque after 60 mins @ -62°C / -80°F	ASTM D1478	Nm	0.02
Low temperature Torque - starting torque @ -73°C / -100°F	ASTM D1478	Nm	0.14
Low temperature Torque - torque after 60 mins @ -73°C / -100°F	ASTM D1478	Nm	0.06
Evaporation Loss (22hrs @ 204°C / 400°F)	ASTM D2595	% wt	0.9
Density of finished grease @ 15°C / 59°F	In-house test	lb/gallon	16.3
Density of finished grease @ 15°C / 59°F	In-house test	g/ml	1950
Specific Gravity Base Oil @ 15°C / 59°F	ASTM D287	-	1.850
Base oil Density @ 15°C / 59°F	ISO 12185 / ASTM D4052	kg/m ³	1850
Base Oil Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm ² /s	45
Base Oil Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm ² /s	140
Base Oil Viscosity @ -54°C / -65°F	ISO 3104 / ASTM D445	mm ² /s	11000
Viscosity Index	ISO 2909 / ASTM D2270	-	350
Pour Point	ISO 3016 / ASTM D97	°C/°F	-72 / -100

Subject to usual manufacturing tolerances.

Braycote 601 EF
04 Aug 2014
Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre, Whitchurch Hill, Pangbourne, Reading, RG8 7QR, United Kingdom

www.castrol.com/industrial